

## **SYNTHETIC ROOFING UNDERLAYMENT (120 GSM)**

<i>PROPERTIES</i>	<i>TEST METHOD</i>	<i>UNIT</i>	<i>VALUES</i>
<b>MECHANICAL PROPERTIES</b>			
Tensile Strength MD (warp)	ASTM D 5035	Kgf	78-82
Elongation (warp)	ASTM D 5035	%	>15
Tensile Strength CD (weft)	ASTM D 5035	Kgf	60-65
Elongation (weft)	ASTM D 5035	%	>15
Tear Strength MD	ASTM D4533	Kgf	23-28
Tear Strength CD	ASTM D4533	Kgf	18-23
<b>PHYSICAL PROPERTIES</b>			
Color	Upper Surface – Grey		
Thickness	ASTM D 1977	mil	10-11
Temperature Range		°F	-40°F to 240°F
COF (kinetic friction)	ASTM D 1894		0.85
COF (static friction)	ASTM D 1895		0.91
Pliability	ASTM D 226		Pass
Fire Rating “Class A”	ASTM E 108		Pass
<b>DURABILITY</b>			
UV Stabilized	Yes		

### FEATURES



**UV Protection**



**Extreme weather Protection**



**Anti-Slip walkable surface**



**Available in various sizes and rolls**



**High temperature tolerance**



**Precision made**

Krishi Geopack Private Limited assumes no liability in connection with the use of this information.